



ALLIN FLAM 100% OKOUME (Euroclass B)



ALLIN
La Motte Michel, 79270 Le Vanneau
Tel.: +33 (0)5 49 35 15 82 / Fax: +33 (0)5 49 35 02 64
contact.allin@groupe-arbor.com / www.allin.fr

p.1/3 - General



Peeled Okoume Veneers 15/10ths
Veneer Quality: II/III
100% Okoume Ply Interiors

Glue: Class 3 - Suitable for use in damp environment
Glue standard: Standard EN 314
Dimensional Tolerance: Standard EN 315
Density: 500 kg/m³ +/- 10%. Standard EN 323

ADVANTAGES

- Fire resistant to European standard Euroclass (B-s2, d0)
- Moisture resistant
- Good mechanical resistance

ON

REQUEST

- + Calibration Value
- - Veneer Quality Value III
- + Veneer Quality Value I
- Varnish, fire retardant paint
- Product certified FSC®

THICKNESS	PLIES	2500 x 1220 mm	3100 x 1530 mm
		Pack size	Pack size
6 mm	5	16 pcs	25 pcs
8 mm	5		
10 mm	5		
12 mm	7		
15 mm	7		
18 mm	9		
22 mm	9		
25 mm	11		
30 mm	13		
40 mm	17		

Delivery quantity tolerance +/- 10%

Applications: Fire-resistant panel for interior and/or exterior design and layout in both public and private areas. Uses: all types including fittings for shops and commercial premises, stands...

Allin Flam 100% Okoume obtains its classification through impregnation. For all varnished, stained and lacquered finishes, please contact us.



La marque de la gestion forestière responsable



DATA SHEET



ALLIN FLAM
100% OKOUME
(Euroclass B)



ALLIN
La Motte Michel, 79270 Le Vanneau
Tel.: +33 (0)5 49 35 15 82 / Fax: +33 (0)5 49 35 02 64
contact.allin@groupe-arbor.com / www.allin.fr

DECLARATION OF PERFORMANCE (DOP)

N° DOP :	DDP GT-31	Version 21 of 01/02/2021
Identification code :	EN 636-3	
Type number :	ALLIN FLAM 100% OKOUME (Euroclass B)	
Intended use :	Use in damp environment	
Manufacturer :	SAS ALLIN - Route de la Couarde - 79270 LE VANNEAU contact.allin@groupe-arbor.com - www.allin.fr	
Evaluation and verification of system performance :	CE 1	
The notified organism :	FCBA 0380	
performed :	initial inspection of the manufacturing facility and control of factory production and monitoring, evaluation and continuous assessment of control of factory production	
delivered :	the factory production control certificate : 0380 – CPR – N°217	

DECLARED PERFORMANCES :

Essential characteristics	Performances															Harmonized technical specification	
			5			8		10	12	15	18		22	25	30		40
Bonding quality	3															EN 13986 : 2004 + A1 : 2015	
Density : Kg/m³	500																
Reaction to fire	B-s2, d0																
Release of formaldehyde	E1																
STRENGTH : N/mm²																	
Bending // to faces			46,0			38,4		33,8	32,2	29,0	33,3		29,9	26,6	25,9		25,1
Bending ⊥ to faces			12,3			19,5		23,9	25,3	26,2	23,8		27,2	30,3	30,8		31,5
Tension // to faces			12,0			9,0		9,6	8,1	9,6	11,9		10,2	9,1	9,0		9,0
Tension ⊥ to faces			9,6			12,5		11,9	13,3	11,8	9,5		11,2	12,2	12,3		12,3
Compression // to faces			19,7			14,8		15,7	13,3	15,7	19,5		16,7	14,9	14,8		14,7
Compression ⊥ to faces			15,8			20,5		19,5	21,9	19,4	15,5		18,3	20,0	20,1	20,2	
Planar shear // to faces			1,3			1,3		1,3	1,3	1,3	1,3		1,3	1,3	1,3	1,3	
Planar shear ⊥ to faces			1,3			1,3		1,3	1,3	1,3	1,3		1,3	1,3	1,3	1,3	
Panel shear			6,0			6,0		6,0	6,0	5,9	5,9		5,9	5,9	5,9	5,9	



ALLIN FLAM
100% OKOUME
(Euroclass B)



ALLIN
La Motte Michel, 79270 Le Vanneau
Tel. : +33 (0)5 49 35 15 82 / Fax : +33 (0)5 49 35 02 64
contact.allin@groupe-arbor.com / www.allin.fr

p.3/3 - DOP

DATA SHEET

Essential characteristics	Performances														Harmonized technical specification		
			5			8		10	12	15	18		22	25		30	40
Thickness in mm																	
ELASTICITY : N/mm²																	
Bending // to faces			7 220			6 020		5 300	5 050	4 770	5 220		4 680	4 160	4 060	3 930	EN 13986 : 2004 + A1 : 2015
Bending ⊥ to faces			1 920			3 060		3 740	3 960	4 200	3 720		4 260	4 740	4 830	4 930	
Tension // to faces			4 970			3 730		3 970	3 350	3 950	4 920		4 220	3 760	3 740	3 710	
Tension ⊥ to faces			3 990			5 190		4 920	5 520	4 900	3 920		4 620	5 060	5 080	5 100	
Compression // to faces			4 970			3 730		3 970	3 350	3 950	4 920		4 220	3 760	3 740	3 710	
Compression ⊥ to faces			3 990			5 190		4 920	5 520	4 900	3 920		4 620	5 060	5 080	5 100	
Planar shear // to faces			67			67		67	67	67	67		67	67	67	67	
Planar shear ⊥ to faces			69			69		68	68	68	67		67	67	67	67	
Panel shear			410			410		410	410	410	410		410	410	410	400	
Punching shear resistance	NPD														EN 13986 : 2004 + A1 : 2015		
Impact resistance	NPD																
Water vapour permeability (μ)																	
- wet cup	45																
- dry cup	180																
Sound absorption [250-500] Hz	0,1																
Sound absorption [1000-2000] Hz	0,3																
Thermal conductivity (W/m.K)	0,13																
Release of pentachlorophenol (ppm)	< 5																

The performance of the product identified is in accordance with the declared performance.

This declaration of performance is issued under the sole responsibility of the manufacturer identified above.

Signed on the behalf of the manufacturer by :	J. ROUSSEAU	Quality Manager	The :	01/02/2021	in :	Le Vanneau
---	-------------	-----------------	-------	------------	------	------------